

EN AW-8176

ASTM 8176 · 8xxx · Al-Fe (past oqim)

BELGILANISHLAR

EN AW EN AW-8176	ASTM / US 8176	DIAMETRLAR 9.0; 9.5 mm	Σ, MPA 60-140
----------------------------	--------------------------	----------------------------------	-------------------------

QO'LLANISH SOHASI

Turar joy va tijoriy binolar uchun qurilish kabellari va o'rnatish simlari.

AFZALLIKLAR

- Kontaktlarda past oqim
- Egiluvchanlik — o'rnatish qulayligi
- UL va IEC talablariga muvofiq
- Misga iqtisodiy samarali muqobil

YETKAZIB BERISH HOLATLARI

HOLAT	DIAMETR, MM	MUSTAHKAMLIK CHEGARASI, MPA	CHO'ZILISH, MIN, %	SOLISHTIRMA QARSHILIK, MAKS, Ω·MM ² /M	O'TKAZUVCHANLIK, MIN, % IACS
F	9.0; 9.5	115-140	10	0.02855	60.4
O	9.5	60-110	30	0.02860	61

KIMYOVIY TARKIB, %

BELGILANISHLAR	MIN %	MAX %
Si	0.030	0.150
Fe	0.400	1.000
Cu	—	0.040
Mn	—	0.030
Zn	—	0.100
Ga	—	0.030
V	—	0.020
Al (Al, min)		qoldiq
Boshqa aralashmalar — har biri		≤ 0.05%

BELGILANISHLAR	MIN %	MAX %
Boshqa aralashmalar — jami		≤ 0.15%

Alusilk
PART OF ITS GROUP
Coiled Aluminium · Connected Future

BOSH OFIS
Dubai Silicon Oasis, Dubai, UAE
+971 50 153 0202
info@alusilk.ae

O'ZBEKISTONDAGI FILIAL
Abdulla Qodiriy ko'chasi, 7 · Yunusobod tumani
· Toshkent
+998 97 341 2222
alusilk.uz · alusilk.ae