

EN AW-8177

ASTM 8177 · 8xxx · Al-Fe (past oqim)

BELGILANISHLAR

EN AW EN AW-8177	ASTM / US 8177	DIAMETRLAR 9.5 mm	Σ , MPA 60-130
----------------------------	--------------------------	-----------------------------	---------------------------------

QO'LLANISH SOHASI

Turar joy va tijoriy qurilishi uchun qurilish kabellari.

AFZALLIKLAR

- Nazorat ostidagi aralashmalar
- Barqaror mexanik xossalar
- Standartlashtirilgan qurilish tizimlari uchun mos

YETKAZIB BERISH HOLATLARI

HOLAT	DIAMETR, MM	MUSTAHKAMLIK CHEGARASI, MPA	CHO'ZILISH, MIN, %	SOLISHTIRMA QARSHILIK, MAKS, $\Omega \cdot \text{MM}^2/\text{M}$	O'TKAZUVCHANLIK, MIN, % IACS
F	9.5	90-130	10	0.02860	61
O	9.5	60-110	25	0.02850	61.2

KIMYOVIY TARKIB, %

BELGILANISHLAR	MIN %	MAX %
Si	—	0.100
Fe	0.250	0.450
Cu	—	0.040
Mn	—	0.010
Mg	—	0.010
Zn	—	0.050
B	—	0.040
Al (Al, min)	qoldiq	
Boshqa aralashmalar — har biri	$\leq 0.03\%$	
Boshqa aralashmalar — jami	$\leq 0.10\%$	

Alusilk

PART OF ITS GROUP

Coiled Aluminium · Connected Future

BOSH OFIS

Dubai Silicon Oasis, Dubai, UAE

+971 50 153 0202

info@alusilk.ae

O'ZBEKISTONDAGI FILIAL

Abdulla Qodiriy ko'chasi, 7 · Yunusobod tumani

· Toshkent

+998 97 341 2222

alusilk.uz · alusilk.ae